

Base fabric:	Polyamide (nylon) woven fabric
Outside coating:	PVC
Inside coating:	PVC
Weight, nominal	390 g/m <sup>2</sup>
Colour (outside / inside)	Red / Red

Physical performance (EN 14325:2018)			
	Test method	Result	Class
Abrasion resistance	EN 530	> 2000 cycles	6 of 6
Flex cracking	EN ISO 7854:B	> 50 000 cycles	6 of 6
Flex cracking @ -30°C	EN ISO 7854:B	> 200 cycles	2 of 6
Tear resistance	EN ISO 9073-4	> 20 N	2 of 6
Tensile strength	EN ISO 13934-1	> 1000 N	6 of 6
Puncture resistance	EN 863	> 50 N	3 of 6
Resistance to flame*	EN 13274-4, meth 3	5 sec	3 of 3
Seam strength	EN 13935-2	> 500 N	6 of 6
<b>Additional tests</b>			
Antistatic properties*	EN 1149-5	t <sub>4</sub> < 4 sec	Pass

\*Not part of the EN 14605 requirements

Barrier performance – Chemical permeation (EN 943-1:2015, EN 14325:2004)		
Chemical	BT (min)	Class
Formaldehyde 37%	> 480	6
Hydrochloric acid 37%	> 480	6
Sodium hydroxide 40%	> 480	6
Sulphuric acid 50%	> 480	6

Tests performed according to ISO 6529, breakthrough criterion 1 µg/cm<sup>2</sup>/min.

Barrier performance – Infective agent penetration (EN 14126:2003)			
	Test method	Result	Class
Resistance to penetration by contaminated blood and body fluids	ISO 16603	No penetration	6 of 6
Resistance to penetration by blood-borne pathogens	ISO 16604	No penetration	6 of 6
Resistance to wet microbial penetration	EN ISO 22610	No penetration	6 of 6
Resistance to biologically contaminated liquid aerosol penetration	ISO DIS 22611	No penetration	3 of 3
Resistance to dry microbial penetration	ISO 22612	No penetration	3 of 3